

TEMASIL 90

DESCRIPTION

A two component, ethyl silicate zinc rich paint.

PRODUCT FEATURES AND RECOMMENDED USES

- ◆ Offers cathodic protection of steel.
- ◆ Excellent resistance to abrasion, weathering and high, dry temperatures (+ 480 °C / 900 °F).
- ◆ Withstands immersion in oils and various solvents. Separate table available.
- ◆ Can be used as a single coat or as a primer for protective coating systems.
- ◆ Recommended for bridges, pipework, heat exchangers and chemical tanks etc.

TECHNICAL DATA

Volume solids 51 ± 2 %

Specific gravity 2.0 kg / l (mixed)

Mixing ratio and product codes

Base	1 part by volume	008 7381-2
Hardener	1 part by volume	008 7380

Pot life 5 hours (23 °C / 74 °F)

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses		Theoretical coverage
dry	wet	
60 µm	120 µm	8.5 m ² /l
80 µm	160 µm	6.4 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying time

DFT 75 µm	+ 10 °C	+ 23 °C	+ 35 °C
Dust dry	½ h	15 min	10 min
Touch dry	1 h	½ h	15 min
Recoatable, RH 85 % *see overleaf	36 h	5 h	2 h
Recoatable, RH 70 %	48 h	24 h	7 h
Recoatable, RH 50 %	-	48 h	24 h

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Finish Matt.

Colours Greenish grey and grey.

TEMASIL 90

APPLICATION DETAILS

Surface preparation	Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4) <u>Steel surfaces:</u> Blast clean to grade Sa2½ - 3. (ISO 8501-1)
Finish	TEMACHLOR 40, TEMACRYL AR, TEMACRYL EA, TEMAL, TEMACOAT GPL-S PRIMER, TEMACOAT GPL-S MIO, TEMACOAT HS PRIMER, TEMACOAT HS 40, TEMACOAT RM 40, TEMACOAT SEALER and TEMACOAT SPA. TEMASIL 90 may be overcoated with above mentioned paints when Thinner 1029 does not dissolve the coat. Before overcoating it is recommended to spray a misty coat with TEMACOAT SEALER or 25 - 30 % thinned TEMACOAT GS 50.
Application conditions	All surfaces must be dry. The temperature of the ambient air or surface should not fall below -15 °C / 5 °F during application and drying. Relative humidity should be 50 - 90 %. The surface temperature of the steel should remain at least 3 °C / 38 °F above the dew point.
Mixing components	First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use a mechanical agitator for mixing.
Application	By airless or conventional spray or brush. Agitate during application. Depending on the application method the paint can be thinned 0 - 5 % by volume. Airless spray nozzle tip 0.018" - 0.021"; spray angle shall be chosen according to the shape of the object. When coating interiors of chemical tanks or working in dry conditions, it is recommendable to rinse the paint film with fresh water 1 - 24 hours after application. Sharp edges, corners, weld seams and other areas difficult to cover properly by spray application should be coated by a brush before the spray application. Note! There is a risk of mudcracking or peeling with heavier coats than approx. 100 µm dry film thickness. Separate application instructions available.
Thinner	Thinner 1029.
Cleaning of equipment	Thinner 1029.
Storage	Avoid to use more than six months old paint (packing date on a label).
VOC	The Volatile Organic Compounds amount to 470 ± 20 g/litre of paint.
HEALTH AND SAFETY	Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Coatings Oy. For professional use only.

tmk230603/008 7380, 008 7381-2